

Gasification



Measurement of Sulfuric Acid Ion by Ion Chromatography

Material: PES (polyether sulfone) Temperature 380 C

Maker	Mold Parts (A)	Mold Parts (B)	Mold Parts (C)	Average Value
Sodick	SO4 2- 19ppm	SO4 2- 17ppm	SO4 2- 11ppm	SO4 2- 15.4ppm
Company A	SO4 2- 264ppm	SO4 2- 237ppm	N/A	SO4 2- 250ppm